

Equivalencias aproximadas entre normas de aceros de calidad

Nº Material EN 10027-2	Denominación DIN V17006-100	Denominación EN 10027-1	Norma EN de referencia
1.0035	St 33	S185	10025
1.0036	Ust 37-2	S235JRG1	10025
1.0037	St 37-2	S235JR	10025
1.0038	RSt 37-2	S235JRG2	10025
1.0044	St 44-2	S275JR	10025
1.0050	St 50-2	E295	10025
1.0060	St 60-2	E335	10025
1.0070	St 70-2	E360	10025
1.0114	St 37-3 U	S235JO	10025
1.0115	K,Q,Z St 37-3 U	S235JOC	10025
1.0116	St 37-3 N	S235K2G3	10025
1.0118	K,Q,Z St 37-3 U	S235J2G3C	10025
1.0120	K,Q,Z St 37-2	S235JRC	10025
1.0121	UQSt 37-2 (Q-Z)	S235JRG1C	10025
1.0122	RQSt 37-2 (Q-Z)	S235JRG2C	10025
1.0128	K,Q,Z St 44-2	S275JRC	10025
1.0138	RoSt 44-3	S275J2H	10210-1
1.0140	K,Q,Z St 44-3 U	S275JOC	10025
1.0141	K,Q,Z St 44-3 N	S275J2G3C	10025
1.0143	St 44-3 U	S275JO	10025
1.0144	St 44-3 N	S275J2G3	10025
1.0149	RoSt 44-2	S275JOH	10210-1
1.0166	St 37-3 Cu 3	S235J2G3Cu	10025
1.0167	RSt 37-2 Cu 3	S235JRG2Cu	10025
1.0242	StE 250-2 Z	S250GD	10147
1.0244	StE 280-2 Z	S280GD	10147
1.0250	StE 320-3Z	S320GD	10147
1.0310	D 10-2	C10D	10016-2
1.0312	St 15	DC05	10130
1.0313	D 8-2	C7D	10016-2
1.0319	RRStE 210.7	L210GA	10208-1
1.0330	St 2. St 12	DC01	10130
1.0332	StW22	DD11	10111
1.0335	StW24	DD13	10111
1.0338	St 4. St 14	DC04	10130

Nº Material EN 10027-2	Denominación DIN V17006-100	Denominación EN 10027-1	Norma EN de referencia
1.0345	HI	P235GH	10028-2
1.0347	RRSt 3, RRSt 13	DC03	10130
1.0392	EK4	DC04EK	10209
1.0402	C 22	C 22	10083-2
1.0406	C 25	C 25	10083-2
1.0413	D 15-2	C15D	10016-2
1.0414	D 20-2	C20D	10016-2
1.0415	D 25-2	C26D	10016-2
1.0425	HII	P265GH	10028-2
1.0429	StE 290.7 TM	L290MB	10208-2
1.0438	BSt 500 S	B500N	10080
1.0445	HIV	P295NH	10028-2
1.0457	StE 240.7	L240NB	10208-2
1.0459	RRStE 240.7	L240GA	10208-1
1,0473	19 Mn6	P355GH	10028-2
1.0481	17 Mn 4	P295GH	10028-2
1.0484	StE 290.7	L290NB	10208-2
1.0486	StE 285	P275N	10028-3
1.0487	WStE 285	P275NH	10028-3
1.0488	TStE 285	P275NL1	10028-3
1.0490	StE 285	S275N	10113-2
1.0491	TStE 285	S275NL	10113-2
1.0493	StE 285	S275NH	10210-1
1.0497	TStE 285	S275NLH	10210-1
1.0501	C 35	C35	10083-2
1.0503	C 45	C45	10083-2
1.0511	C 40	C40	10083-2
1.0516	D 35-2	C38D	10016-2
1.0517	D 45-2	C48D	10016-2
1.0518	D 55-2	C56D	10016-2
1.0528	C 30	C30	10083-2
1.0529	StE 350Z	535ODG	10147
1.0530	D 30-2	C32D	10016-2
1.0533	ZSt 50-2	E295GC	10025
1.0535	C 55	C55	10083-2
1.0539	StE 355	535 5NH	12010-1

Nº Material EN 10027-2	Denominación DIN V17006-100	Denominación EN 10027-1	Norma EN de referencia
1.0540	C 50	C50	10083-2
1.0541	D 40-2	C42D	10016-2
1.0543	ZSt 60-2	E355GC	10025
1.0545	tE 355	S355N	10113-2
1.0546	TStE 355	S355NL	10113-2
1.0549	TStE 355	S355NLH	10210-1
1.0553	St 52-3 U	S355JO	10025
1.0554	K,Q,Z St 52-3 U	S355JOC	10025
1.0562	StE 355	P355N	10028-3
1.0565	WStE 355	P355NH	10028-3
1.0566	TStE 355	P355NL1	10028-3
1.0569	K,Q,Z St 52-3 N	S355J2G3C	10025
1.0570	St 52-3 N	S355J2G3	10025
1.0576	RoSt 52-3	S355J2H	10210-1
1.0578	StE 360.7 TM	L36OMB	10208-2
1.0582	StE 360.7	L36ONB	10208-2
1.0585	St 52-3 Cu 3	S355J2G3Cu	10025
1.0586	D 50-2	C50D	10016-2
1.0588	D 53-2	C52D	10016-2
1.0601	C 60	C60	10083-2
1.0609	D 58-2	C58D	10016-2
1.0610	D 60-2	C60D	10016-2
1.0611	D 63-2	C62D	10016-2
1.0612	D 65-2	C66D	10016-2
1.0613	D 68-2	C68D	10016-2
1.0614	D 75-2	C76D	10016-2
1.0615	D 70-2	C70D	10016-2
1.0616	D 85-2	C86D	10016-2
1.0617	D 73-2	C72D	10016-2
1.0618	D 95-2	C92D	10016-2
1.0620	D 78-2	C78D	10016-2
1.0622	D 80-2	C80D	10016-2
1.0626	D 83-2	C82D	10016-2
1.0628	D 88-2	C88D	10016-2
1.0633	SZt 70-2	E360GC	10025
1.0971	QStE 260 N	S260NC	10149-3

Nº Material EN 10027-2	Denominación DIN V17006-100	Denominación EN 10027-1	Norma EN de referencia
1.0972	QStE 300 TM	S315MC	10149-2
1.0973	QStE 300 N	S315NC	10149-3
1.0976	QStE 360 TM	S355MC	10149-2
1.0977	QStE 360 N	S355NC	10149-3
1.0980	QStE 420 TM	S420MC	10149-2
1.0981	QStE 420 N	S420NC	10149-3
1.0982	QStE 460 TM	S460MC	10149-2
1.0984	osis 500 TM	S500MC	10149-2
1.0986	QStE 550 TM	S550MC	10149-2
1.1104	EStE 285	P275NL2	10028-3
1.1106	EStE 355	P355NL2	10028-3
1.1149	Cm 22	C22R	10083-1
1.1151	Ck 22	C22E	10083-1
1.1158	Ck 25	C25E	10083-1
1.1163	Cm 25	C25R	10083-1
1.1170	28 Mn 6	28Mn6	10083-1
1.1178	Ck 30	C30E	10083-1
1.1179	Cm 30	C30R	10083-1
1.1180	Cm 35	C35R	10083-1
1.1181	Ck 35	C35E	10083-1
1.1186	Ck 40	C40E	10083-1
1.1189	Cm 40	C40R	10083-1
1.1191	Ck 45	C45E	10083-1
1.1201	Cm 45	C45R	10083-1
1.1202	D 53-3	C52D2	10016-4
1.1203	Ck 55	C55E	10083-1
1.1206	Ck 50	C50E	10083-1
1.1209	Cm 55	C55R	10083-1
1.1212	D5 8-3	C58D2	10016-4
1.1220	D 55-3	C56D2	10016-4
1.1221	Ck 60	C60E	10083-1
1.1222	D 63 -3	C62D2	10016-4
1 1223	Cm 60	C60R	10083-1
1.1228	D 60 -3	C60D2	10016-4
1.1232	D6 8-3	C68D2	10016-4
1.1236	D 65 -3	C66D2	10016-4

Nº Material EN 10027-2	Denominación DIN V17006-100	Denominación EN 10027-1	Norma EN de referencia
1.1241	Cm 50	C50R	10083-1
1 1242	D 73 -3	C72D2	10016-4
1.1252	D7 8-3	C78D2	10016-4
1.1253	D 75 -3	C76D2	10016-4
1.1255	D 80 -3	C80D2	10016-4
1.1262	D 83 -3	C82D2	10016-4
1.1265	D 85 -3	C86D2	10016-4
1.1272	D8 8-3	C88D2	10016-4
1.1282	D 95 -3	C92D2	10016-4
1.3401	X120 Mn 12	X120Mn12	-
1.4301	X5 CrNi 18 10	X4CrNi18-10	10088
1.4541	X6 CrNiTi 18 10	X6CrNiTi18-10	10088
1.5415	15 Mo 3	16Mo3	10028-2
1.5530	21 MnB 5	20MnB5	10083-3
1.5531	30 MnB 5	30MnB5	10083-3
1.5532	38 MnB 5	38MnB5	10083-3
1.5631	10 N i 14	12Ni14	10028-4
1.5662	X 8 Ni 9	X8Ni9	10028-4
1.5680	12 Ni 19	X12Ni5	10028-4
1.7035	41 Cr 4	41Cr4	10083-1
1.7039	41Cr54	41Cr54	10083-1
1.7131	16 MnCr5	16MnCr5	10084
1.7218	25 CrMo 4	25CrMo4	10083-1
1.7220	34 CrMo 4	34CrMo4	10083-1
1.7225	42 CrMo 4	42CrMo4	10083-1
1.7226	34 CrMoS 4	34CrMoS4	10083-1
1.7227	42 CrMoS 4	42CrMoS4	10083-1
1.7335	13 CrMo 4 4	13CrMo4-5	10028-2
1.7380	10 CrMo 9 10	10CrMo9-10	10028-2
1.8159	50 Cr V4	51CrV4	10089
1.8823	StE 355 TM	S355M	10113-3
1.8825	StE 420 TM	S420M	10113-3
1.8827	StE 460 TM	S460M	10113-3
1.8834	TStE 355 TM	S355ML	10113-3
1.8836	TStE 420 TM	S420ML	10113-3
1.8838	TStE 460 TM	S460ML	10113-3

Nº Material EN 10027-2	Denominación DIN V17006-100	Denominación EN 10027-1	Norma EN de referencia
1.8901	StE 460	S460N	10113-2
1.8902	StE 420	S420N	10113-2
1.8903	TStE 460	S460NL	10113-2
1.8905	StE 460	P460N	10028-3
1.8912	TStE 420	S420NL	10113-2
1.8915	TStE 460	P460NL1	10028-3
1.8918	EStE 460	P460NL2	10028-3
1.8925	EStE 890 V	S890QL1	10137-2
1.8928	T5SE 690 V	S690QL	10137-2
1.8931	StE 690 V	S690Q	10137-2
1.8933	TStE 960 V	S960QL	10137-2
1.8935	WStE 460	P460NH	10028-2
1.8953	StE 460	S460NH	10210-1
1.8956	TStE 460	S460NLH	10210-1
1.8961	WTSt 37-3	S235J2W	10155
1.8963	WTSt 52-3	S355J2G1W	10155
1.8983	TStE 890 V	S890QL	10137-2
1.8988	EStE 690 V	S690QL	10137-2